



FABRASORB® II

FABRASORB® II Acoustical Membrane

FABRASORB is a trademark for a family of acoustically absorptive membranes used as liners in SHEERFILL® architectural membrane systems. A FABRASORB membrane serves not only to attenuate sound but also to enhance the thermal characteristics of fabric roof systems. The performance of FABRASORB materials with respect to permanent building codes is consistent with that of SHEERFILL architectural membranes. FABRASORB products are translucent, non-burning, porous composites based on fiberglass and polytetrafluoroethylene.

Typical Properties¹

Property	Value	Method
Coated Fabric Weight (oz./yd. ²)	8.5 nominal	ASTM D4851-88
Thickness (mils)	9.0 nominal	ASTM D4851-88
Breaking Strength (lb./in.) (Strain Rate: 2 in./min.) Dry, Warp Dry, Fill	210 min avg 180 min avg	ASTM D4851-88
Breaking Strength After Crease Fold (lb./in.) Dry, Warp Dry, Fill	195 min avg 165 min avg	ASTM D4851-88
Trapezoidal Tear (lb.) Warp Fill	17 min avg 18 min avg	ASTM D4851-88
Solar Transmission (%)	27 nominal	ASTM E424
Solar Reflectance (%)	65 nominal	ASTM E424
Burning Characteristics Flame Spread Smoke Generation	5 max 15 max	ASTM E84 Tunnel Test
Incombustibility of Substrates	Pass	ASTM E136
Flame Resistance	Pass	NFPA 701, Small Scale
Sound Absorption, Octave Band Center Frequency, Hz 250 500 1000 2000 4000 Absorption Coefficient, SABINS/ft ² (Nominal) 0.4 0.4 0.6 0.6 0.7	NRC 0.55	ASTM C423
Color	White	
Reinforcement Construction	Warp β150 1/2, Fill β150 1/2-Count W42 x F32	

¹- Values listed are for virgin roll goods only. Appropriate industry safety factors need to be used to account for the in-service effects of handling, weathering, etc.

Saint-Gobain Performance Plastics

701 Daniel Webster Highway
Merrimack, NH 03054

Customer Service: (800) 451-6101

Tel: (603) 424-9000

Fax: (603) 424-9012

www.sheerfill.com

www.fff.saint-gobain.com

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

FABRASORB® and SHEERFILL® are registered trademarks.
©2005 Saint-Gobain Performance Plastics Corporation
AFF-1028-1M-0205-SGCS